



ORIGINAL ARTICLE

Open Access



# Comparison of the elastic limit and yield load of nailed joints connecting solid wood and wood-based board material

Naoki Watanabe<sup>1</sup>, Keita Ogawa<sup>2\*</sup> and Kenji Kobayashi<sup>2</sup>

## Abstract

Evaluations of the lateral properties of timber joints are necessary to ensure the safety of timber buildings. The yield load is an important property that is usually obtained using authorized engineering techniques. Although yield loads have been easily obtained using authorized techniques, events that have occurred in the joint during yielding have not been clarified. This study experimentally obtains elastic limit data using nailed joints. Mechanical tests measuring the residual displacement after various lateral loads with six-joint specimen specifications were conducted. In this study, the load at which the residual displacement reached 5% of the nail diameter was defined as the elastic limit. The experimentally obtained elastic limits were compared with the yield loads obtained using authorized engineering techniques. The ratios of elastic limits to the yield loads obtained using the perfect elasto-plastic model, method described in EN, and 5% offset method were 0.554–0.743, 0.557–0.834, and 0.648–0.801, respectively. The results numerically revealed that residual displacements occurred at a much lower load than the yield loads.

**Keywords:** Nailed joint, Residual displacement, Yield load, Elastic limit

## Introduction

Nailed joints connecting solid wood and board materials are commonly used in timber structures. A widely known example is the panel-sheathed shear wall, which connects a wooden frame and board materials with nails. Several researchers have revealed that the in-plane shear performance of a shear wall is dominated by the lateral resistance of nailed joints. Tuomi and McCutcheon blazed the trail of mechanical analyses estimating the shear strength of shear walls using the lateral loading test results of nailed joints [1]. Several researchers have attempted to develop a mechanical model for estimating the elasto-plastic behavior of walls using the test results of nailed joints [2–6]. In the mechanical models constructed in these studies, the wooden frame and board material were

regarded as rigid bodies; their results revealed that the shear deformation of the wall can be expressed by the slip deformation of the nailed joints. Some studies have included other factors (e.g., the shear buckling of board materials [7, 8], the bending of a wooden frame [9, 10], and a pull-out of a column form beam [11]) in their mechanical models; however, the consensus is that the slip of nailed joints is a main factor in the deformed wall. Recently, the structural design method, which enables the calculation of the shear properties of walls using the lateral properties of nailed joints, has been proposed and has become widely used [12, 13].

Evaluating the lateral resistance of nailed joints has been an important issue in the academic and practical areas of timber structures for several years. Many tests have been conducted, and a large quantity of characteristic data has been collected [14]. The yield load is one of the most important characteristics for designing structural timber elements. The yield load is known as the load value, and is located just over the elastic limit of the

\*Correspondence: ogawa.keita@shizuoka.ac.jp

<sup>2</sup> College of Agriculture, Academic Institute, Shizuoka University, 836 Ohya, Suruga-ku, Shizuoka 422-8529, Japan  
Full list of author information is available at the end of the article

load–deformation relationship; moreover, it represents the starting point of plastic deformation. However, for timber joints, the yield point is difficult to decipher visually from the load–deformation relationship because the relationship shows a gradual shift from elastic to plastic behavior. Therefore, engineering techniques for determining the yield load from the relationship (their details are described later) have been proposed worldwide. These techniques enable the objective evaluation of joint properties.

Although engineering techniques have contributed to the development of academic knowledge and practical timber structures, problems remain. Researchers and engineers who use these techniques can obtain the yield load; however, the true mechanical situation of the joint at the obtained load is unclear. The authors emphasize the importance of clarifying what occurs in the joint at the obtained yield load. Accordingly, the authors have attempted to collect various experimental data to clarify what occurs at the load regarded as the yielding point. This study focuses on the residual displacement and compares the starting point of residual displacement (the so-called elastic limit [15]) with the yield load as determined by engineering techniques.

**Materials and methods**

**Nailed joint specimen**


A nailed joint specimen [16] for the lateral load was prepared, as shown in Fig. 1. Two side panels were mounted on the main member with four nails. Three wood species with different densities were chosen as the main members: Japanese cedar (*Cryptomeria japonica*), spruce, and Japanese larch (*Larix kaempferi*). For preparing the spruce specimen, the authors bought several lots of SPF

dimension lumber, and picked out spruce from them. The authors confirmed that Engelmann spruce (*Picea engelmannii*) was included, but other types of spruce might be included in the lots. The densities are listed in Table 1. The size of the main member was 38 × 89 mm by cross section and 300 mm in length. Structural plywood with a 5-ply and a 12 mm thickness made of Japanese cedar, representing class 2 structural plywood according to JAS [17], and structural medium density fiberboard (MDF) of a 9-mm thickness, classified as type M-30 according to JIS [18], were used as side panels. The size of the side panels was 100 × 300 mm. CN50 nails [19], with a trunk diameter of 2.87 mm and a length of 50.8 mm, were used to connect the main member and side panels. Therefore, using three species of main members and two types of side panels, this study conducted tests with six specifications of the nailed specimen. For specimens using plywood, the plywood was set so that the fiber direction of the outer veneer was parallel to the loading direction. A Teflon sheet and grease were inserted to remove the friction between the main member and side panel, as shown in Fig. 1. According to our previous study, the coefficient of friction becomes 0.1 or lower with the method [20]. Therefore, the effect of friction was ignored in our upcoming discussion of the test results.

**Loading methods**

A lateral loading test was conducted using a universal testing machine (Shimadzu Co. Ltd., AG-1 250 kN). A downward load is applied to the top face of the main member, as shown in Fig. 1. Thus, a slip between the main member and side member occurred. In this study, two loading methods were applied. The first was to evaluate the yield load of the joints using authorized engineering techniques, and the second was to measure the residual displacement.


The first loading method used was monotonic loading, which is commonly utilized to evaluate the lateral resistance of timber joints. A downward load with a continuous loading speed was applied from the start to the end of testing, and the expected load–displacement relationship



**Table 1** Average and standard deviation of densities of test materials

Materials	Density (kg/m <sup>3</sup> )
Japanese cedar	385.6 ± 29.5
Spruce	453.8 ± 47.8
Japanese larch	531.8 ± 41.8
Structural plywood	410.9 ± 14.1
Structural MDF	802.1 ± 15.0





The second method is described in EN 12512 [26] (referred to as EN). As shown in Fig. 3b, the direct Line I was drawn between  $0.1 P_{\max}$  and  $0.4 P_{\max}$ . Next, the second Line II was drawn so that its incline became 1/6 of the incline of Line I and it meets the load–displacement relationship. The load value at the intersection of Lines I and II represents the yield load.

The third method is described in ASTM D5652-21 [27] (referred to as OSM). Although the method is for bolted joints, it was also applied to nailed joints [28]. To determine the yield load, a straight line was fitted to the initial linear portion of the load–displacement curve. In the ASTM standard, there are no precise descriptions of the method for drawing a straight line. In this study, the authors drew the line using the least squares method for the data plots between  $0.1 P_{\max}$  to  $0.4 P_{\max}$ . The line was offset by a displacement of 5% of the nail diameter. The yield load represents the load at which the offset line intersects the load–displacement relationship, as shown in Fig. 3b.

Johansen theory [29], which is well known as European yield theory (EYT) in Japan, is the most popular method to obtain the yield load using material characteristic values. The Architectural Institute of Japan [30] following Johansen theory, and yield load  $P_y$  was calculated using the following equation:

$$P_y = C \cdot F_e \cdot d \cdot l, \quad (1)$$

$$C = \min \left\{ \begin{array}{l} \frac{1}{\sqrt{2 + \frac{8}{3}\gamma \left(\frac{d}{l}\right)^2} - 1}, \\ \frac{d}{l} \sqrt{\frac{8}{3}\gamma} \end{array} \right.$$

$$\alpha = l'/l, \quad \beta = F_e'/F_e, \quad \gamma = F/F_e,$$


where  $F_e$  and  $F_e'$  indicate the embedment strengths of the main member and board material, respectively.  $F$

indicates the nail strength.  $d$  indicates the nail diameter.  $l$  and  $l'$  indicate the inserted length of the nail in the main member and thickness of the board material, respectively. The authors additionally conducted embedment tests and bending test [31] for calculating the yield load with the equation. Figure 4a shows the experimental setup of embedment test for solid wood. Clear wood specimens were cut from the joint specimens, and the embedment load parallel to the grain was applied with a nail to the top surface of the specimen. Ten replicates were assigned to each wood species. Figure 4b shows the experimental setup of embedment test for board material. Small board material specimens were obtained from the joint specimens. With fixing the lower part with a bolt, a nail inserted to the upper part was loaded upward. During the embedment tests, load and displacement were recorded. Ten replicates were assigned to each board type. Figure 4c shows the bending test for nail. Three-point bending test with the span of 32 mm was conducted. After conducting these tests, strength was obtained from load–deformation relationship. As the same with OSM, the straight line for initial stiffness was offset by a displacement of 5% of the nail diameter. The load at which the offset line intersects the load–displacement relationship was used for obtaining the strength [31]. For obtaining the embedment strengths, stress was calculated by dividing the load by loading area. For obtaining the nail strength, the bending stress was calculated with the load. In this study, the calculated yield load is denoted as EYT.

## Results and discussion

### Yield load obtained via the monotonic loading test

The load–displacement relationships are shown in Fig. 5. In all specifications, a straight linear behavior was observed at the beginning of loading. The slope of the relationship gradually decreased with an increase in displacement. After reaching the maximum load, the load gradually decreased, and no brittle failures occurred in



any of the specimens. Regarding the differences in materials, the specifications using the main member with the highest density showed the highest resistance. The specifications using MDF showed a higher resistance than that of the plywood. For MDF, the displacement at the maximum load appeared to be smaller than that of the plywood. Although the specimens using plywood reached their maximum load at approximately 15–20 mm in displacement, many specimens using MDF reached a maximum load less than 10 mm in displacement, especially for cedar–MDF and spruce–MDF.

The averages and standard deviations of the yield loads obtained using the three techniques are listed in Table 3. In comparing the differences between the techniques, the EPM shows the highest value and OSM shows the lowest value in most of specifications. A multiple comparison test (Bonferroni method) was conducted to verify the difference due to the techniques. The significant differences between EPM and OSM were recognized in all of specifications, a significant difference between EPM and EN were recognized in the specification of cedar–MDF, and a significant difference between EN and OSM were recognized in the specification of larch–plywood at a significant level 0.05. The results indicate that the yield load may differ depending on what was chosen by the users. On the load–displacement relationships in Fig. 5, the yield loads obtained using EPM, EN and OSM are plotted with yellow round, red rhombus, and blue squares, respectively. The yield load from EPM was plotted where the load–displacement relationships started to decrease in slope. This result was also observed in previous study by one of the authors [32].

The values used to calculate EYT are listed in Table 4, which are average values obtained from the embedment


tests and bending test. The calculated results are listed in Table 3. Although the following is not the direct purpose of this study, the authors touch about the comparisons between EYT and the other yield loads. The EYT is higher than the OSM in all the specifications. In the specifications using plywood, EYT is higher than EPM, whereas similar or lower yield loads can be observed in the cases using MDF. The reason for the difference between the EYT and experimentally obtained values has not been clarified in this study, but one possible reason is that the values of EYT were obtained with the assumption that the materials behave as rigid-plastic, which may differ from actual behavior especially in the cases using low-embedment strength materials.

#### Load–deformation relationship and residual displacements obtained by the reversed loading test

Examples of load–deformation relationships are shown in Fig. 6. For a small target load, the relationship during loading shows linear behavior, and relatively minimal residual displacement is observed after unloading. The gradual decrement of the slope in the linear relationship and large residual displacement were observed using the increment of the target load (e.g.,  $P_t = 0.25$  kN or more in Fig. 6a,  $P_t = 0.60$  kN or more in Fig. 6b).

The residual displacements obtained from the load–displacement relationships are shown in Fig. 7. The round plots indicate the mean value at each target load and the error bars indicate the standard deviation. For example, in the cedar–plywood (Fig. 7a), when the target load was lower than 0.30 kN, the residual displacements appeared to be small and could be regarded as almost zero. However, when a target load of over 0.30 kN occurred, the plots were separated from the horizontal





**Fig. 5** Load–displacement relationships and yield points obtained via the monotonic loading test. The vertical axis indicates the load per a nail. The graphs were drawn for each specimen specification

axis. With an increase in the target load, the residual displacement exponentially increased. From the results, the elastic limit [15] seems to be approximately 0.30 kN. The specifications with the highest yield loads exhibited the highest elastic limits. For example, the elastic limit for larch–MDF was approximately 0.50 kN in the target load.

#### Comparison of elastic limit and yield loads obtained using various methods

To compare the elastic limit and yield loads, it was necessary to obtain an accurate value of the elastic limit. According to Goodno and Gere [15], the elastic limit

represents the load that will be reached wherein all the displacement is recovered during unloading. Based on the load–displacement relationship (Fig. 6), it is difficult to search for the target load in which the residual displacement is perfectly zero, because a small residual displacement will appear even for a small target load. There is no authorized method for defining the elastic limit; therefore, this study calculated the elastic limit as the load when the residual displacement became 5% of the nail diameter. The average values (plots in Fig. 7) were linearly interpolated to determine the load at which the residual displacement was 0.1435 mm.

**Table 3** Yield loads obtained using multiple methods

Specification	EPM <sup>a</sup> (kN)	EN <sup>b</sup> (kN)	OSM <sup>c</sup> (kN)	EYT <sup>d</sup> (kN)
Cedar–ply-wood	0.465 ± 0.054	0.417 ± 0.042	0.391 ± 0.035	0.569
Cedar–MDF	0.614 ± 0.034	0.571 ± 0.025	0.561 ± 0.021	0.626
Spruce–ply-wood	0.514 ± 0.048	0.471 ± 0.061	0.440 ± 0.033	0.571
Spruce–MDF	0.654 ± 0.060	0.592 ± 0.053	0.576 ± 0.052	0.630
Larch–ply-wood	0.531 ± 0.038	0.533 ± 0.076	0.473 ± 0.038	0.598
Larch–MDF	0.743 ± 0.084	0.673 ± 0.058	0.639 ± 0.054	0.668


<sup>a</sup> Yield load obtained using the perfect elasto-plastic model<sup>b</sup> Yield load obtained using the method described in EN 12512 [26]<sup>c</sup> Yield load obtained using the offset method<sup>d</sup> Yield load obtained using European yield theory

The elastic limits are presented in Table 5. For the specification using plywood, the elastic limits were 0.282, 0.285, and 0.297 kN. When MDF was used, the elastic limits were 0.476, 0.420, and 0.512 kN, respectively. A possible reason for the difference in values is that plywood is a material that easily undergoes residual deformation, so the elastic limits of joints using plywood are dominated by the wood's properties. Although spruce–MDF showed a higher yield load than cedar–MDF in the monotonic loading test, a lower elastic limit occurred. This suggests that the elastic limit is not directly related to the yield load. However, this research used only three species of main members, and additional tests with more species are required to ensure a reliable discussion.

Table 5 also lists the ratios of the elastic limit to the yield loads. In most specifications, the ratios were less than 1, which means that the elastic limit was sufficiently lower than the yield loads. For EPM, the ratios at specification using plywood were 0.554–0.606, thereby suggesting that residual displacement occurs in almost half of the EPM. The ratios of the specifications using MDF were 0.642–0.743, which were higher than that of plywood. Similar values were observed for the ratios of EN and EYT. Although the yield load of OSM was lower than


those of EPM and EYT (Table 3), the elastic limits were lower than those of OSM, and the ratios were 0.628–0.801. These results reveal that the residual displacements of the nailed joints were much lower than those of the yield loads.

Finally, the residual displacements occurred at the yield loads were calculated. The results are listed in Table 6. The average values (plots in Fig. 7) were linearly interpolated to determine the residual displacement at yield load. From the table, it is revealed that non-negligible displacements are remained at the yield loads. In the joints using plywood, residual displacement became over 1 mm when the yield loads were determined with European yield theory. Although OSM was a lowest yield load, 0.284–0.687 mm remained at the load. Currently, it is difficult to judge

**Fig. 6** Examples of load–displacement relationships obtained via the reversed loading test. The legends denote the target load per a nail**Table 4** Material properties used for calculating EYT

Specification	$F_e$ (N/mm <sup>2</sup> )	$F_e'$ (N/mm <sup>2</sup> )	$F$ (N/mm <sup>2</sup> )	$d$ (mm)	$l$ (mm)	$l'$ (mm)
Cedar–plywood	28.7	24.9	997.5	2.87	38.8	12
Cedar–MDF	28.7	37.6	997.5	2.87	41.8	9
Spruce–plywood	29.3	24.9	997.5	2.87	38.8	12
Spruce–MDF	29.3	37.6	997.5	2.87	41.8	9
Larch–plywood	37.4	24.9	997.5	2.87	38.8	12
Larch–MDF	37.4	37.6	997.5	2.87	41.8	9

$F_e$  and  $F_e'$ : embedment strength of main member and board material,  $F$ : strength of nail;  $d$ : diameter on nail,  $l$  and  $l'$ : inserted length of nail in the main member and thickness of the board material, respectively



**Fig. 7** Relationships between the residual displacement and target load per a nail. The plot and error bar indicate the mean value and standard deviation at each target load, respectively

clearly whether the residual displacement in Table 6 is a serious matter for the safety of timber structures or not. If it becomes a serious matter, the new evaluating technique of yield load which shows the lower yield load than presenting methods will be required.

## Conclusion

The residual displacements of nailed joints under lateral loads were experimentally measured, and relevant elastic limits were obtained. These elastic limits were approximately 0.3 kN in the cases of joints using plywood



**Table 5** Elastic limit and the ratio of the elastic limit to the yield loads obtained using engineering techniques

Specification	Elastic limit (kN)	Ratio of elastic limit to yield loads			
		EPM	EN	OSM	EYT
Cedar–plywood	0.282	0.606	0.676	0.721	0.496
Cedar–MDF	0.476	0.743	0.834	0.731	0.760
Spruce–plywood	0.285	0.554	0.605	0.648	0.499
Spruce–MDF	0.420	0.642	0.709	0.729	0.667
Larch–plywood	0.297	0.559	0.557	0.628	0.497
Larch–MDF	0.512	0.689	0.761	0.801	0.766

**Table 6** Residual displacement at each yield load (unit: mm)

Specification	EPM	EN	OSM	EYT
Cedar–plywood	0.589	0.403	0.372	1.363
Cedar–MDF	0.413	0.305	0.284	0.455
Spruce–plywood	0.817	0.596	0.512	1.398
Spruce–MDF	0.694	0.384	0.353	0.562
Larch–plywood	1.282	1.311	0.687	2.270
Larch–MDF	0.676	0.417	0.351	0.407

as a side panel. For MDF, the elastic limits were 0.420–0.512 kN, which differed from the species used in the main member. In comparing the elastic limits with yield loads obtained with widely used techniques, the formers were much lower than the latter; the ratios of elastic limits to the yield load with the perfect elasto-plastic model, method described in EN, and 5% offset method were 0.554–0.743, 0.557–0.834, and 0.648–0.801, respectively. The results also showed that residual displacements occurred at much lower loads than the yield loads. It was also revealed that non-negligible displacements remained after yielding. Especially, the residual displacement become over 1 mm in the case of nailed joints using plywood when the yield load is determined with European yield theory.

#### List of symbols

$P_t$ : Target load;  $P_{max}$ : Maximum load;  $P_y$ : Yield load;  $F_e$ : Embedment strengths of the main member;  $F_{e'}$ : Embedment strengths of the board material;  $F$ : Nail strength;  $d$ : Nail diameter;  $l$ : Inserted length of the nail in the main member;  $t$ : Thickness of the board material.

#### Author contributions

NW and KO designed and performed the experiments and analyzed the data. KK participated in the discussions on data interpretations. NW and KO wrote the manuscript in consultation with KK. All authors read and approve the final manuscript.

#### Funding

Not applicable.

#### Availability of data and materials

All data discussed during this study are included in this published article.

#### Declarations

#### Competing interests

The authors declare that they have no competing interests.

#### Author details

<sup>1</sup>Bioresource Sciences Course, Department of Agriculture, Graduate School of Integrated Science and Technology, Shizuoka University, 836 Ohya, Suruga-ku, Shizuoka 422-8529, Japan. <sup>2</sup>College of Agriculture, Academic Institute, Shizuoka University, 836 Ohya, Suruga-ku, Shizuoka 422-8529, Japan.

Received: 10 March 2022 Accepted: 3 July 2022

Published online: 16 July 2022

#### References

- Tuomi RL, McCutcheon WJ (1978) Racking strength of light-frame nailed walls. *J Struct Div* 104:1131–1140
- Kamiya F (1981) Theoretical studies on racking stiffness and strength of wooden sheathed walls. *Trans AIJ* 56:86–94
- Easley JT, Foomani M, Dodds RH (1982) Formulas for wood shear walls. *J Struct Eng* 108:2460–2478
- McCutcheon WJ (1985) Racking deformations in wood shear walls. *J Struct Eng* 111:257–269
- Schmidt RJ, Moody RC (1989) Modeling laterally loaded light-frame buildings. *J Struct Eng* 115:201–207
- Ogawa K, Sasaki Y, Yamasaki M, Fukuta S (2015) Theoretical estimation of mechanical properties of plywood-sheathed shear wall with combined use of adhesive tape and wood dowels. *Wood Fiber Sci* 47:421–430
- Murakami M, Azumi Y, Oshita Y (2015) Experimental study on relationship between shear buckling and shear failure of nailed sheathed shear walls. *J Struct Constr Eng, AIJ* 80(716):1569–1578
- Murakami M, Azumi Y (2017) Study on structural calculation method of nailed sheathed shear walls under shear force considering shear buckling and shear failure of sheets. *J Struct Constr Eng, AIJ* 82(732):239–246
- Gupta AK, Kuo GP (1985) Behavior of wood-framed shear wall. *J Struct Eng* 111:1722–1733
- Murakami M, Azumi Y, Inayama M (2012) Formula to predict shear stiffness of sheathed wall considering flexural stiffness of vertical studs and its verification with numerical analyses. *J Struct Constr Eng, AIJ* 77(672):249–258
- Sudo R, Kawahara H, Ochiai Y, Aoki K, Inayama M (2021) Detailed verification on the performance of nailed joints in the panel sheathed shear wall. *J Struct Constr Eng, AIJ* 86(784):945–956
- Murakami M, Inayama M (1999) Formulae to predict the elastic and plastic behavior of sheathed walls with any nailing arrangement pattern. *J Struct Constr Eng, AIJ* 519:87–93
- Working group for revising the manuscript of the allowable stress design for wooden framework method (2017) In: Committee for revising the allowable stress design for wooden framework method (ed) Allowable stress design for wooden framework method. Japan Housing and Wood Technology Center, Tokyo
- Ogawa K (2018) Domestic studies on shear resistance of nailed timber joint. *Mokuzai Kogyo* 73(1):2–7
- Goodno BJ, Gere JM (2017) Elasticity, plasticity, and creep. In: *Mechanics of materials*, 9th ed SI. Cengage learning, Connecticut, pp 38–44
- JAS 0360 (2019) Structural panel. Japan Agricultural Standard. [https://www.maff.go.jp/j/jas/jas\\_kikaku/attach/pdf/kikaku\\_itiran2-334.pdf](https://www.maff.go.jp/j/jas/jas_kikaku/attach/pdf/kikaku_itiran2-334.pdf). Accessed 10 May 2022
- JAS (2019) Plywood. Japan Agricultural Standard. [https://www.maff.go.jp/j/jas/jas\\_kikaku/attach/pdf/kikaku\\_itiran2-235.pdf](https://www.maff.go.jp/j/jas/jas_kikaku/attach/pdf/kikaku_itiran2-235.pdf). Accessed 10 May 2022
- Japanese standards association (2014) Fiberboard JIS A 5905, Tokyo
- Japanese standards association (2009) Nails JIS A 5508, Tokyo

20. Ogawa K, Mori R, Kobayashi K (2021) Verification of general methods for inhibiting friction used in mechanical tests of timber joints. *Mokuzai Kogyo* 76(10):376–381
21. Yasumura M, Kawai N (1998) Estimating seismic performance of wood-frame structures. In: *Proceedings of the 5th world conference on timber engineering (WCTE)*. Montreal, Switzerland, 1998, 564–571
22. Wanyama OG, Sawata K, Hirai T, Koizumi A, Sasaki Y (2012) Effective lateral resistance of timber–plywood–timber joints connected with nails. *J Wood Sci* 58:315–321
23. Ueda R, Sawata K, Takanashi R, Sasaki Y, Sasaki T (2020) Degradation of shear performance of screwed joints caused by wood decay. *J Wood Sci* 66:42
24. Ogawa K, Fukuta S, Kobayashi K (2020) Experimental study of lateral resistance of bolted joints using Japanese cedar (*Cryptomeria japonica*) treated with resin impregnation. *J Wood Sci* 60:71
25. Kržan M, Azinović B (2021) Cyclic response of insulated steel angle brackets used for cross-laminated timber connections. *Eur J Wood Prod* 79:691–705
26. EN 12512 (2002) Timber structures—test methods—cyclic testing of joints made with mechanical fasteners. European Committee for Standardization (CEN), Brussels
27. ASTM D5652-21 (2021) Standard test method for single-bolt connections in wood and wood-based products. ASTM International, West Conshohocken.
28. Sawata K, Sasaki Y (2018) Lateral strength of nailed timber connection with decay. *J Wood Sci* 64:1734
29. Johansen KW (1948) Theory for timber connection. *Int Assoc Bridge Struct Eng* 9:249–262
30. Yasumura M (2011) Timber joints using dowel type connections. In: *Architectural Institute of Japan (ed) Standard for structural design of timber structures*. Maruzen publishing, Tokyo, pp 222–238
31. Kawai N (2011) General test method for joints. In: *Architectural Institute of Japan (ed) Standard for structural design of timber structures*. Maruzen publishing, Tokyo, pp 369–376
32. Ogawa K, Harada M, Shibusawa T, Miyamoto K (2018) Single shear properties and deformation behavior of nailed joints using various structural panel materials. *Mokuzai Gakkaishi* 64(4):139–148

## Publisher's Note

Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

**Submit your manuscript to a SpringerOpen<sup>®</sup> journal and benefit from:**

- Convenient online submission
- Rigorous peer review
- Open access: articles freely available online
- High visibility within the field
- Retaining the copyright to your article

---

Submit your next manuscript at ► [springeropen.com](https://www.springeropen.com)